

# Ozone Bitulastic CA

Single component rubberized bitumastic sealant

<b>Description</b>	Ozone Bitulastic CA is a single component, solvent based, rubberized bitumastic joint sealant. The sealant on curing form a tough and flexible long lasting joint sealant. Provide watertight joints, particularly in conditions of permanent immersion. The mastic sealant is modified with special additives which makes it ideal for both horizontal and vertical areas.																				
<b>Uses &amp; Benefits</b>	<ul style="list-style-type: none"><li>▪ Excellent adhesion to concrete, cementitious mortars, wood, glass and metal surfaces.</li><li>▪ Resist high water pressure and suitable for contact with drinking water.</li><li>▪ Used on concrete slabs and decks, water retaining structures, tunnels and culverts, basements and irrigation channels, retaining walls, roofing and cladding, open water retaining structures.</li><li>▪ For water tight sheet piling interlocks.</li><li>▪ Firm flexible weather resistant seal.</li><li>▪ Excellent immersed adhesion.</li></ul>																				
<b>Properties</b>	<table><tr><td>Color :</td><td>Black</td></tr><tr><td>Specific gravity :</td><td>1.40</td></tr><tr><td>Consistency :</td><td>Non-slump ASTM C639-5</td></tr><tr><td>Form:</td><td>Paste</td></tr><tr><td>Solid content:</td><td>80%</td></tr><tr><td>Setting time:</td><td>24-48 hours</td></tr><tr><td>Movement capacity:</td><td>15%</td></tr><tr><td>Chemical resistance :</td><td>Sea water, chlorides, sulphate ions, diluted alkalis, diluted acids</td></tr><tr><td>Application temperature:</td><td>5 to 45°C</td></tr><tr><td>Service temperature:</td><td>-15 to 80°C</td></tr></table>	Color :	Black	Specific gravity :	1.40	Consistency :	Non-slump ASTM C639-5	Form:	Paste	Solid content:	80%	Setting time:	24-48 hours	Movement capacity:	15%	Chemical resistance :	Sea water, chlorides, sulphate ions, diluted alkalis, diluted acids	Application temperature:	5 to 45°C	Service temperature:	-15 to 80°C
Color :	Black																				
Specific gravity :	1.40																				
Consistency :	Non-slump ASTM C639-5																				
Form:	Paste																				
Solid content:	80%																				
Setting time:	24-48 hours																				
Movement capacity:	15%																				
Chemical resistance :	Sea water, chlorides, sulphate ions, diluted alkalis, diluted acids																				
Application temperature:	5 to 45°C																				
Service temperature:	-15 to 80°C																				
<b>Packaging</b>	15 Kg, 20 Kg Pails.																				
<b>Storage</b>	Store in a dry and cool place below 35°C. Protect from direct sunlight.																				
<b>Shelf life</b>	12 months if stored in original unopened packaging																				
<b>Instruction for use</b>	<p><b>Surface preparation:</b> All joints should be thoroughly cleaned and any foreign matter blown out. All old caulk or sealant should be removed. Care should be taken to remove any surface alkaline deposit from cement or concrete .Clean all glass or aluminum surfaces with a mineral spirit or mild solvent prior to apply the sealant.</p> <p><b>Application:</b> Ozone Bitulastic CA is applied to the joint by trowel, spatula or by hand. Neither any primer nor pre-heating of the product is required.</p>																				
<b>Cleaning &amp; Disposal</b>	Clean tools and hands with soapy water. Do not dispose off into water or soil but according to local regulations.																				
<b>Precautions &amp; Limitations</b>	Do not use on dusty or damp surfaces.																				
<b>Health &amp; Safety</b>	Ozone Bitumastic CA is not classified as dangerous. During application wear suitable protective clothing, gloves and eye protection.																				

**WARRANTY:** Ozone products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. Ozone makes no warranties, implied or otherwise, as to the merchantability or fitness for ordinary or particular purposes of its products and excludes the same. If any Ozone product fails to conform with this warranty, Ozone will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made period from the date of the claimed breach. Ozone does not authorize anyone on its behalf to make any written or oral statements which in any way alter Ozone's installation information or instructions in its product literature or on its packaging labels. The user of the Ozone products must test the products for suitability for the intended application and purpose before proceeding with the full application of the products.